

ALLOY 718

APPLICABLE SPECIFICATIONS

API6A CRA, UNS NO7718, NACE MR 0175/ISO15156, W2.4668

A versatile nickel chromium alloy, exhibiting high strength and excellent corrosion resistance. Used in a range of demanding environments such as the oil & gas sector and other critical industries.

TYPICAL APPLICATIONS

Valves & actuators, sealing products, surface wellhead components, downhole drilling.

CHEMICAL ANALYSIS RANGE (WT%) (AS PER API6A CRA)

Ni	50.00 - 55.00	C	0.045 Max	Cu	0.23 Max
Cr	17.00 - 21.00	Co	1.00 Max	Pb	0.0010 Max
Fe	Balance	Mn	0.35 Max	Se	0.0005 Max
Nb (Cb) + Ta	4.87 - 5.20	Si	0.35 Max	Bi	0.00005 Max
Mo	2.80 - 1.15	P	0.010 Max	Ca	0.003 Max
Ti	0.80 - 1.15	S	0.010 Max	Mg	0.006 Max
Al	0.40 - 0.60	B	0.0060 Max		

HEAT TREATMENT

SQA bar stock is in the Solution Annealed and Aged condition to meet the requirements of NACE MR-0175/ISO15156 2nd Edition – 40 HRC Max. Other heat treatment conditions available on request.

TYPICAL MECHANICAL PROPERTIES IN SOLUTION ANNEALED & AGED CONDITION (AS PER API6A CRA)

0.2% Yield Strength	120000 PSI min
Tensile Strength	150000 PSI min
Elongation	20% min
Reduction of Area	35% min
Hardness	40 HRC Max
Charpy V Notch @ -60 DEG C	68 Joules min average (Longitudinal)
(For sections up to 10")	47 Joules min average (Transverse)
(For sections above 10")	41 Joules min average (Transverse)

The data contained in this publication is for informational purposes only and may be revised at any time without prior notice. The data is believed to be accurate and reliable, but Special Quality Alloys makes no representation or warranty of any kind (express or implied) and assumes no liability with respect to the accuracy or completeness of the information contained herein. Although the data is believed to be representative of the product, the actual characteristics or performance of the product may vary from what is shown in this publication. Nothing contained in this publication should be construed as guaranteeing the product for a particular use or applications

